

## AD-here® LOF 65-00

Technical Data Sheet	
Description	AD-here® LOF 65-00 is a liquid anti-stripping agent derived from amidoamines. It increases the adhesion of asphalt cement to aggregate and reduces the potential for moisture damage. It also improves the retention of aggregates in chip seals. AD-here® LOF 65-00 unique property is its low odor characteristics.
Typical Properties	Appearance: Brown Viscous Liquid Typical Viscosity, 77°F: 900 cps Typical Viscosity, 100°F: 300 cps Density, Pounds/Gallon, 77°F: 8.05 Flash Point (P.M.C.C.): > 300°F
Features	<ul style="list-style-type: none"> <li>• Very effective in reducing stripping and in increasing the tensile strength values in the AASHTO T-283, ASTM D4867, or similar test methods.</li> <li>• Low odor and low smoke generation at elevated temperatures when compared to most liquid anti-strips, therefore, lower fume exposure for paving crews.</li> <li>• AD-here® LOF 65-00 can also be used as an adhesion promoter in anionic emulsions to enhance aggregate coating.</li> <li>• Very effective in improving aggregate retention on chip seals.</li> <li>• Increases the wetting ability of asphalt cements and cutback asphalts.</li> <li>• DOT Shipping Non-Regulated.</li> <li>• Non Corrosive</li> </ul>
Applications	AD-here® LOF 65-00 is added to the asphalt cement, typically in the amount of 0.25 - 1.0% by weight of the asphalt cement. The specific dosage should be based on a laboratory design method, such as AASHTO T-283.
Packaging	AD-here® LOF 65-00 is available in bulk quantities (1000 - 5500 gal.) and in 55 gallon non-returnable drums (420# net). It is available from our four manufacturing locations: Mulberry, Florida; Convent, Louisiana; Soda Springs, Idaho; and Vanceboro, North Carolina.
Storage and Handling	Refer to MSDS prior to handling this material. Avoid water contamination during handling and storing. For ease of pumping it is recommended to keep the product at 100° - 120°F.
TSCA Compliance	N/A

All suggestions and data are based on information and tests we believe to be reliable. Insofar as applications by prospective users may differ from those recommended, it is suggested the user conduct tests and determine the suitability of the product to his process. No warranty for the application of this product is expressed or implied.